



FILM WASHI
world's smallest film company

P
100 ISO
DATA SHEET

HANDCOATED BLACK & WHITE FILM

Sensitivity : 100 ISO
Grain : fine
Contrast : medium
Production process : handcoating
Base : Polyester, 100 µm
Spectral sensitivity : maximum 640 nm
Darkroom safelight : full darkness



Special features : "P" is a prototype panchromatic film handcoated on transparent polyester base. With no anti-halation layer it can give, under special light conditions, a very nice effect of diffusion.

Recommended use : Portrait, still life, landscape and all classic subjects.

Processing :

exposure	developer	dilution	time	T°C
100 iso	Rodinal	1+25	9 mn	20°C
100 iso	LC29	1+19	8 mn	20°C
100 iso	D76	1+1	11 mn	20°C
100 iso	HC-110	A	4,5 mn	20°C

For using with an unlisted developer, you can use times and dilution data of Ilford FP4.

Structure of layers :



Loading : load 135 under shadow to avoid light piping.
120 roll films can be loaded as usual.

Standard sizes : 120/620 spool
135 recycled cassette (no DX code) – 16 exp.
Use of recycled cassette is not recommended with full automatic/motorized camera.
custom sizes available on demand

Usage tips : The diffusion effect can change depending of the light conditions, it is also much stronger in 135 than in 120 format.

.....
We take great care in the manufacture of each Film. If you are unhappy with the film for any reason please get in touch and we will do our best to help. In case of manufacturing defect, films will be replaced by new ones. No other claims for compensation will be accepted.