




## HANDCRAFTED PANCHRO FILM ON KOZO PAPER

Maximum sensitivity: 100 ISO **Texture:** very strong Contrast: soft

**Production process:** hand coating Kozo paper, 28 gr/m<sup>2</sup> Base: Transparency: medium

Spectral sensitivity: maximum 640 nm Darkroom safelight: full darkness



**Special features:** "Y" is a panchromatic film handcoated on Kozo paper made in Japan, it is an improved version of film "Y" offering higher sensitivity and wider lattitude exposure.

Recommended use: Sensitive to all colors, this film is a great choice to shoot landscapes with a unique pictorialist effect, but also portraits and all classic

subjects.

120 roll films can be loaded like any normally. Loading & handling:

> While unloading the roll, it is advised to secure it with a rubber band or scotch tape.

Formats: 120 spool

**Exposure:** Being coated with a real film emulsion, "Y" has a nominal sensitivity

of 100 iso but can be pushed or pulled by 2 stops, like any other classic film.

Tank processing: Paper based films must be loaded following tutorial available on

www.filmwashi.com .

However, it is still possible to use dedicated separating stripe system produced by Film Washi and also old tanks like "Correx" or "Souplinox".

## **Exposure settings & processing times:**

exposition	révélateur	dilution	durée	T°C
100 iso	Rodinal	1+25	9 mn	20°C
100 iso	LC29	1+19	8 mn	20°C
100 iso	D76	1+1	11 mn	20°C
100 iso	HC-110	Α	4,5 mn	20°C
For using with an unlisted developer, you can use times and dilution data				

of Ilford FP4.

Structure of layers: sensitive emulsion Kozo paper base anti-curl back layer

Scan: Film "Y" can be scanned by transparency, like any other negative.

Usage tips: 120 rolls are handspooled and few very delicate camera can have issue to handle it.

> Please never force on the winding lever and contact Film Washi for any question.

We take great care in the manufacture of each Film. If you are unhappy with the film for any reason please get in touch and we will do our best to help. In case of manufacturing defect, films will be replaced by new ones. No other claims for compensation will be accepted.