

ORTHOCHROMATIC BLACK & WHITE LEADER FILM

Sensitivity:

12 ISO

Grain:

fine

Contrast:

very strong

Production process:

industrial coating

Base:

polyester, 120 µm

Spectral sensitivity:

maximum 580 nm

Darkroom safelight:

red, 620 nm



Original use:

"A" is normally used as leader and protection tail for motion picture film copy, but also for recording sub-titles or main-titles.

Recommended use:


portrait, urban photography, still life, astrophotography.

Processing:

exposure	developer	dilution	time	T°C
12 iso	Ilfotec LC29	1+19	7 mn	20°C
12 iso	Ilfotec RT rapid	---	70 s	26°C
12 iso	Rodinal	1+50	13 mn	20°C
12 iso	D-76	1+1	9 mn	20°C
12 iso	Xtol	stock	5,5 mn	20°C
25 iso	Tetenal Eukobrom	1+1	4 mn	20°C

For use with an unlisted developer, you can use, for a 12 iso exposure, time and dilution for the Ilford Delta at 400 iso.

Structure of layers:



Loading:

Under shadow. To avoid light piping effect, take 3 blank pictures before starting your roll.

Standard sizes:

135 recycled cassette (no DX code) – 36 exp.

Use of recycled cassettes is not recommended with fully automatic/motorized cameras.

30,5m bulk roll

Usage tips:

Beware of too much contrast with outdoor views: the sky can be easily overexposed. For interior shooting, please remind that this film is not very sensitive to tungsten type light: natural light will give much better results.

We take great care in the manufacture of each Film. If you are unhappy with the film for any reason, please get in touch and we will do our best to help. In case of manufacturing defect, films will be replaced by new ones. No other claims for compensation will be accepted.